

Technical data sheet CPE+

Ultimaker
It's in the making

Chemical Name	Copolyester
Description	CPE+ is chemical and temperature resistant, tough and demonstrate good dimensional stability. CPE+ shows higher temperature resistance and increased impact strength than regular CPE.
Key features	Excellent chemical resistance, temperature resistance, toughness and dimensional stability, good interlayer adhesion (especially when using the front door add-on), good bed adhesion (especially when using the adhesion sheets), and low levels of ultrafine particles (UFPs) and volatile organic compounds (VOCs). Allows printing of translucent parts with the transparent filament option.
Applications	Visual and functional prototyping and short run manufacturing.
Non suitable for	Food contact and in-vivo applications. Long term outdoor usage or applications where the printed part is exposed to temperatures higher than 100 °C.

Filament specifications

	<u>Value</u>	<u>Method</u>
Diameter	2.85±0.10 mm	-
Max roundness deviation	0.10 mm	-
Net filament weight	700 g	-

Color information

<u>Color</u>	<u>Color code</u>
CPE+ Transparent	n/a
CPE+ Black	RAL 9005
CPE+ White	RAL 9010 (est.)

Mechanical properties (*)

	<u>Injection molding</u>		<u>3D printing</u>	
	<u>Typical value</u>	<u>Test method</u>	<u>Typical value</u>	<u>Test method</u>
Tensile modulus	1575 MPa	ASTM D638	1129 MPa	ISO 527 (1 mm/min)
Tensile stress at yield	43 MPa	ASTM D638	35 MPa	ISO 527 (50 mm/min)
Tensile stress at break	52 MPa	ASTM D638	33 MPa	ISO 527 (50 mm/min)
Elongation at yield	7 %	ASTM D638	6 %	ISO 527 (50 mm/min)
Elongation at break	210 %	ASTM D638	6.6 %	ISO 527 (50 mm/min)
Flexural strength	64 MPa	ASTM D790	-	-
Flexural modulus	1575 MPa	ASTM D790	-	-
Izod impact strength, notched (at 23°C)	860 J/m	ASTM D256	-	-
Charpy impact strength (at 23°C)	-	-	-	-
Hardness	111 (Rockwell)	ASTM D785	-	-

Thermal properties

	<u>Typical value</u>	<u>Test method</u>
Melt mass-flow rate (MFR)	-	-
Heat deflection (HDT) at 0.455 MPa	94 °C	ASTM D648
Heat deflection (HDT) at 1.82 MPa	81 °C	ASTM D648
Glass transition	-	-
Coefficient of thermal expansion (flow)	-	-
Coefficient of thermal expansion (xflow)	-	-
Melting temperature	-	-
Thermal shrinkage	-	-

Other properties

	<u>Typical value</u>	<u>Test method</u>
Specific gravity	1.18	ASTM D792
Flame classification	-	-

(*) See notes.

Notes

Properties reported here are average of a typical batch. The 3D printed tensile bars were printed in the XY plane, using the normal quality profile in Cura 2.1, an UM2+, a 0.4 mm nozzle, 90% infill, 260 °C nozzle temperature and 110 °C build plate temperature. The values are the average of 5 natural, 5 white and 5 black tensile bars. Ultimaker is constantly working on extending the TDS data.

Disclaimer

Any technical information or assistance provided herein is given and accepted at your risk, and neither the Ultimaker or its affiliates make any warranty relating to it or because of it. Neither Ultimaker nor its affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness of your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product; and nothing herein waives any of Ultimaker's conditions of sale. Specifications are subject to change without notice.

Version

Version 3.005

Date

21/10/2016

Ultimaker
It's in the making